

SCOPE

Life sciences (pharmaceutical industry, hospitals), industry.

Three-layer inner CSM/intermediate polyurethane/outer CSM glove. Excellent resistance to chemicals and to ionising radiation, ozone and UV. Good mechanical resistance.





IN COMPLANCE WITH 2016/425 EUROPEAN REGULATION (CATEGORY 3 P.P.E.)



SC-COM-189- Rev 1

((0333 FRD22588 LOT) 30/06





GENERAL INFORMATION

Chemical composition	Chlorosulfonated Polyethylene / Polyurethane / Chlorosulfonated Polyethylene	
Material code	Y/PUR/Y	
Colour	White	
Packaging	Individually packed in two-toned black and transparent, heat-sealed and easy-opening pouch. Pack of 30 units.	
Care instructions	Store in the original packaging between +5°C and +25°C. Expiry date of 3 years in the original packaging. Wash with soapy water, rinse with clear water and then air-dry at a low temperature (<40°C).	
Treatment	Non-recyclable. Disposal as simple non-toxic waste if not contaminated by a hazardous substance.	
Sterilisation	Can be delivered in a decontaminated version or a decontaminated- sterilised version (sterilisation with Gamma radiation) (pack of 50 units).	
Powdering	Standard: lightly powdered gloves.	
Disinfectants	Excellent resistance to the following disinfectants: 0.25% Surfanios, 10% Soproper, 70% Isopropyl alcohol.	
Dimensional tolerances	Thickness: 5/10 mm (palm min 3.5/10, max 7/10). Length: 330 mm. Diameter of the rim: 4 mm (+/-1 mm).	

PHYSICOCHEMICAL PROPERTIES TEMPERATURE RANGE: -20 TO +120°C			
Alcohols			
Acids, bases			
Strong oxidants			
Uv, ozone, free radicals, natural ageing			
Ketone solvents			
Chlorinated solvents			
Aromatic solvents			
Aliphatic oils and solvents			
Peracétic acid sterilisation (3%)			
H202 Sterilisation (35%)			
H2O2 Sterilisation (50%)			
25-50 kGray gamma radiation			
Autoclave sterilisation (121°c)			
Protection from ionising radiation			
* ——— Not recommanded ——— Can be used under certain conditions ——— Acceptable ——— Recomme	nded		

The instruction leaflet, the EU Declaration of Conformity and the list of references are available on the website.

MECHANICAL PROPERTIES 100% Modulus ⁽¹⁾ Tensile strength ⁽¹⁾ Elongation at break ⁽¹⁾ Puncture (EN 388)					
< 3.0 MPa	> 15 MPa	> 300%	> 30 N		
(1) (Iso 37 type 2)					

PIERCAN

17-23 rue Marcel Dassault CS 10028 - 93 141 BONDY CEDEX, France T:+33 (0)1 45 88 66 27 - F:+33 (0)1 45 80 98 30 www.piercan.fr - piercan@piercan.fr



